

# UNITED STATES AIR FORCE RESEARCH LABORATORY



## HIGH BRIGHTNESS EMISSIVE MINIATURE DISPLAY DEVELOPMENT

Gary Jones

e MAGIN CORPORATION  
2070 ROUTE 52  
HOPEWELL JUNCTION NY 12533

JANUARY 2003

20031112 120

FINAL REPORT FOR THE PERIOD 14 JULY 1998 TO 31 AUGUST 2002

Approved for public release; distribution is unlimited.

Human Effectiveness Directorate  
Crew System Interface Division  
2255 H Street  
Wright-Patterson AFB OH 45433-7022

## NOTICES

When US Government drawings, specifications, or other data are used for any purpose other than a definitely related Government procurement operation, the Government thereby incurs no responsibility nor any obligation whatsoever, and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Please do not request copies of this report from the Air Force Research Laboratory. Additional copies may be purchased from:

National Technical Information Service  
5285 Port Royal Road  
Springfield, Virginia 22161

Federal Government agencies and their contractors registered with the Defense Technical Information Center should direct requests for copies of this report to:

Defense Technical Information Center  
8725 John J. Kingman Road, Suite 0944  
Ft. Belvoir, Virginia 22060-6218

## DISCLAIMER

This Technical Report is published as received and has not been edited by the Air Force Research Laboratory, Human Effectiveness Directorate.


## TECHNICAL REVIEW AND APPROVAL

AFRL-HE-WP-TR-2003-0014

This report has been reviewed by the Office of Public Affairs (PA) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public.

This technical report has been reviewed and is approved for publication.

## FOR THE COMMANDER

  
BRIAN P. DONNELLY, Lt Col, USAF  
Deputy Chief, Crew System Interface Division  
Air Force Research Laboratory

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE January 2003		3. REPORT TYPE AND DATES COVERED FINAL REPORT 14 July 1998 to 31 August 2002
4. TITLE AND SUBTITLE  High Brightness Emissive Miniature Display Development			5. FUNDING NUMBERS  PR: 7184    PR: 7184 TA: 11      TA: 11 WU: FE      WU: 15	
6. AUTHOR(S)  Gary Jones*				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  *eMagin Corporation 2070 Route 52 Hopewell Junction NY 12533			8. PERFORMING ORGANIZATION	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  Air Force Research Laboratory Human Effectiveness Directorate Crew System Interface Division Air Force Materiel Command Wright-Patterson AFB OH 45433-7022			10. SPONSORING/MONITORING  AFRL-HE-WP-TR-2003-0014	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  The program thrust was material/device development, to improve the thermal characteristics of OLED materials so that they can withstand more heating without deterioration, and to improve the efficiency of the devices so that less heat is generated. Additionally, the program was to engineer a better thermal management strategy, to remove generated heat quickly and effectively, thus limiting the temperature rise in the OLED device.				
14. SUBJECT TERMS  Miniature Flat Panel Display, AMOLED, OLED, Active Matrix Organic Light Emitting Diode, Organic Light Emitting Diode			15. NUMBER OF PAGES 5	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT  Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE  Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT  Unclassified	20. LIMITATION OF ABSTRACT  Unlimited	

This Page Intentionally Left Blank

# High Brightness Emissive Miniature Display Development

## Introduction

This development program was created in response to an RFP from the Dual Use Science and Technology Program of DoD. Organic light emitting diode (OLED) displays had been demonstrated to have many of the characteristics which are desirable in helmet mounted displays. They are light, efficient, capable of good contrast at high resolution, and have Lambertian emission characteristics, an important feature for use with magnifying optics. OLEDs were also known to be capable of very high brightnesses ( $> 30,000 \text{ cd/m}^2$ ) in pulsed operation, even though they would tend to overheat and suffer irreversible deterioration when operated at such brightnesses for extended periods. For certain helmet applications, namely projection of information by reflection from a clear plastic visor, such high brightnesses are required on a sustained basis, so this became a requirement to extend OLED technology to allow it to fulfill this type of application.

eMagin Corporation, together with Eastman Kodak Company and Honeywell Corporation, proposed to achieve the required technology extension by a dual-pronged approach. One thrust of the program was material/device development, to improve the thermal characteristics of OLED materials so that they can withstand more heating without deterioration, and to improve the efficiency of the devices so that less heat is generated. The second thrust of the program was to engineer a better thermal management strategy, to remove generated heat quickly and effectively, thus limiting the temperature rise in the OLED device. Significant progress toward these goals has been achieved, as has been reported in the series of milestone reports over the course of the program.

New materials were developed to replace the conventional hole transport materials, which were subject to deterioration at any temperature over  $100^\circ \text{C}$ . New device structures, based upon a better management of internal barriers, allowed a demonstration of improved efficiency, even for the most well known emitter material,  $\text{Alq}_3$ . Also, simulation analysis of the thermal dissipation in proposed device packages, by eMagin, coupled with an analysis by Honeywell of a system for dissipating heat in a helmet, led to the conclusion that the heat load expected in high brightness operation could in fact be managed without reaching excessive temperatures at the OLED display.

In other words, all of the ingredients for meeting the needs of a high brightness projection microdisplay for helmets have been demonstrated, short of building an actual packaged high brightness display, which would have required a new chip that is not yet available.

## Materials Development

Hole Transport Materials – When this work was undertaken, the most widely used hole transport materials for making OLED devices were CuPc (Copper Phthalochanine) and NPB (naphthalene phenyl benzidine), used in a layered combination. Devices made in this way were unstable at temperatures greater than 100° C, due to crystallization of the NPB. The tendency of an amorphous material to crystallize is best quantified by the glass transition temperature,  $T_g$ , which in the case of NPB is about 95° C.

We set as a goal the development of suitable hole transporters capable of use at temperatures up to 130° C. Of course, there are requirements other than  $T_g$  which a hole transport layer (HTL) material must meet. The material must have a HOMO (highest occupied molecular orbital) energy that is in a suitable range between about 5.0 eV for a material used close to the anode and 5.5 eV for a material used adjacent to an emitter such as Alq<sub>3</sub>. Also, the LUMO (lowest unoccupied molecular orbital) energy of the HTL material must be less than about 2.7 eV, to stop electrons at the HTL/emitting layer (EML) interface. A final requirement relates to evaporability. Typically, higher  $T_g$ s can be achieved with larger molecules, but larger molecules generally require higher evaporation temperatures. If the evaporation temperature becomes too high, decomposition may occur, resulting in a layer with uncertain composition and stability.

In the course of this work, many new materials were synthesized and evaluated, and these have been reported in detail in the earlier reports. Most interesting of these were HT-306, an attractive hole injector layer (HIL) material, and HT-308, an excellent replacement for NPB. HT-308 was shown in experiments at Kodak to be more stable than NPB, even at moderate temperatures of operation. Its HOMO and LUMO energies are similar to those of NPB, which is not surprising, since it can be viewed as a composite of NPB structural elements.

Since we were focused on achieving better performance from OLEDs at higher temperatures, we also evaluated new materials from commercial OLED material suppliers. Some of these turned out to be very good, and they have the advantage of easy availability, whereas we do not have production capability for materials developed by us. Among these materials are a spiro-triaryl diamine (S-TAD) from Covion, which is well suited as an HIL material, as well as IDE-406 and IDE-320, from Idemitsu Kosan Co., which are excellent HTL materials. IDE-320, like our HT-308, is a high  $T_g$  (>130° C) material with electronic properties very close to those of NPB. This material was developed partly at our request.

Emitter Materials - On the emitter side, Kodak tried various approaches to achieving a green efficiency superior to that of Alq<sub>3</sub>, the standard. Some carbazole compounds were thought to be attractive until they were found to be lacking in stability under operation. Kodak also explored the phosphorescent dopant approach introduced by the Princeton/USC collaboration. As detailed in

our earlier reports, this system turns out to have superior efficiency at low luminances, but at the very high luminances required in this program it is not as efficient as a conventional fluorescent dopant system, namely coumarin in Alq<sub>3</sub>. For this reason, we ended up concluding that for a very high brightness green OLED display, Alq<sub>3</sub> doped with coumarin or with dimethylquinacridone (DMQA) is the best choice today.

OLED Devices – Using combinations of these selected materials, we were able to achieve quantum efficiencies of nearly 15 cd/A even at the highest luminances required. In an up-emitting configuration, this should translate to a power efficiency of about 1.8 lumens/Watt, even at 30,000 cd/m<sup>2</sup> (Efficiencies, of course, are much higher at low luminances). For an SXGA microdisplay with 5% of the pixels lit (a Honeywell estimate for typical helmet use), this would translate into a power level of only 0.5 W.

### **Thermal Management**

As detailed in Milestones 19B and 20, experimental and theoretical analysis of the thermal characteristics of a packaged OLED-on-silicon microdisplay revealed that, with a suitable heat sink and chip bonding process, the temperature rise in the OLED relative to the temperature of the heat sink could be maintained at a very acceptable level. Specifically, the temperature rise of the OLED was found to be less than 0.5° C per Watt dissipated in the OLED. Even for a worst case scenario, where the display had all pixels lit, the power would reach about 10W, causing a temperature rise of only 5° C.

The problem in the worst case scenario would be getting the heat out of the helmet; 10W is probably unmanageable. However, for any reasonable fraction of lit pixels the problem is manageable. For example, a 20% fill factor (4 times Honeywell's estimated fill factor) would result in a power level of about 2W, and a Honeywell design for a feasible heat sink system would result in a temperature rise for the heat sink relative to ambient air of about 20° C in the moving air assumed in a cockpit environment. This would be added to the 1° C rise in the package for a 2W load, totaling 21° C. Given the improvements in the thermal characteristics of the materials described earlier, this would not present a serious problem. For the more realistic estimate of 5% pixel usage factor, the total temperature rise over ambient is only about 5° C.

### **Summary**

We have successfully established in this program that even the exceptional demands of a visor-projection type helmet mounted microdisplay can be met with OLED technology, using the proper combination of OLED materials, device structure, device packaging, and helmet heat sink design. In this way, the other benefits of the OLED approach can be gained: simplicity, light weight, resolution, contrast, large exit pupil, etc.